

**TECHNICAL
DATA SHEET**

 PSR-9000 FLX03G/CA-90 FLX03G
 MS-00261401
 MS-00261501
 Feb.2016

1/4



PSR-9000 FLX03G/CA-90 FLX03G

(UL Suffix: PSR-9000AD / CA-90AD)

1. FEATURES

PSR-9000 FLX03G/CA-90 03G is two component, liquid photoimageable solder resist (alkaline developable type) with following features:

- a) Excellent flexibility
- b) Flamed-retardant type
- c) Environment conscious with Halogen Free

2. SPECIFICATION

Main agent	PSR-9000 FLX03G
Hardener	CA-90 FLX03G
Color*	Green
Mixing ratio	Main agent : 75 / Hardener : 25 (By weight)
Viscosity*	180dPa/s (Cone plate Viscometer, 5min ⁻¹ / 25deg.C)
Solid Content*	73.0wt%
Tack dry window*	80deg.C / 60min (Maximum)
Exposure energy*	Metal Halide lamp : 280 - 420mJ/cm ² (On solder mask) High mercury short arc lamp : 400 - 600mJ/cm ² (On solder mask)
Pot life*	24 hours (Stored in dark place, at below 25deg.C)
Shelf life	6 months (Stored in dark place at below 20deg.C)

*: After mixing

TECHNICAL DATA SHEET

 PSR-9000 FLX03G/CA-90 FLX03G
 MS-00261401
 MS-00261501
 Feb.2016

2/4

3. PROCESS CONDITION

Process		Range
PWB	Espanex M-grade (CU:18um, PI:25um) Kapton 25um	
Pre-treatment	Espanex : Acid treatment – water rinse Kapton : No pre-treatment	
Printing	#100-mesh Tetron screen	100-150mesh
Hold time	10min	10-20min
Tack dry	<ul style="list-style-type: none"> ➤ Both sides simultaneous exposure 1st printing : 80deg.C/15min 2nd printing : 80deg.C/25min (Hot air convection oven) ➤ Single side exposure 80deg.C/ 30min (Hot air convection oven) 	80deg.C/20-30min 80deg.C/20-35min 80deg.C/30-40min
Exposure	Metal halide lamp 7kw (ORC HMW-680) 350mJ/cm ² (on solder mask) Mercury short arc lamp 500mJ/cm ² (on solder mask)	280-420mJ/cm ² 400-600mJ/cm ²
Hold time	10min	10-20min
Development	Aqueous alkaline solution : 1 wt% Na ₂ CO ₃ Temperature of developer : 30deg.C Spray pressure : 0.2MPa Developing time : 60sec	0.20-0.25MPa 60-90sec
Water rinse	Temperature of rinsing water : 25deg.C Spray pressure : 0.1MPa Rinsing time : 45sec	Below 25deg.C 0.1-0.15MPa 60-90sec
Post cure	150deg.C / 60min (Hot air convection oven)	30-90min

*In case of applying marking ink, solder mask should be cured at 150deg.C for 30 minutes, then marking ink should be cured at 140deg.C for 20 minutes x 2 cycles. In case no marking ink is applied, solder mask should be cured at 150deg.C for 60 minutes.

4. ATTENTION IN PROCESS:

- As to the operation environment. It is desirable to deal with the ink under the yellow lamps in the clean room. Please avoid using it under white fluorescent lamps or sunlight (directly or indirectly).
- After confirmation that ink becomes room temp., please start mixing in accordance with required amount of mixing ratio.
- The adequate thickness is 10 - 20 um (on the copper after curing). Thin coating possibly reduces its solder heat resistance. On the other hand, thick coating possibly causes the under-cut or low tackiness.

TECHNICAL DATA SHEET

 PSR-9000 FLX03G/CA-90 FLX03G
 MS-00261401
 MS-00261501
 Feb.2016

3/4

- Please set the pre-cure conditions and tack dry window after the confirmation test because they are influenced according to the type of the drying machine and the quantity of the board to be dried.
- Please set the exposing energy after the confirmation test of under-cut, surface gloss, back side exposure and so on because it is influenced according to the material of the board, the thickness of ink, etc.
- Regarding the developing process, please control the developer density, the temperature, the spray pressure and the developer time, etc. The inadequacy of control causes the degradation of the developability and the increase of under-cut.
- Please set the post cure conditions considering the curing time of the marking ink. Insufficient curing or over curing may cause the degradation of properties.
- In order to ensure ENIG resistance, please set up appropriate post cure conditions with considering final baking of marking ink. ENIG resistance could be deteriorated due to over baking.

5. CHARACTERISTIC

(1) TACK DRY WINDOW

Drying time (80deg.C / min)	30	40	50	60	70
Developability	Clean	Clean	Clean	Clear	Residue

(2) PHOTSENSITIVITY: Metal halide lamp 7kw

Item	Thickness	Energy	Developing time	Sensitivity
Sensitivity Kodak No.2 (Step density tablet)	21 +/- 2um	280mJ/cm ²	60 sec.	5 step
		350mJ/cm ²		6 step
		420mJ/cm ²		7 step

The exposure energy is measured below Mylar film (on solder mask)

(3) PHOTSENSITIVITY: Mercury short arc lamp

Item	Thickness	Energy	Developing time	Sensitivity
Sensitivity Kodak No.2 (Step density tablet)	21 +/- 2um	400mJ/cm ²	60 sec.	4 step
		500mJ/cm ²		5 step
		600mJ/cm ²		5 step

The exposure energy is measured below Mylar film (on solder mask)

**TECHNICAL
DATA SHEET**

 PSR-9000 FLX03G/CA-90 FLX03G
 MS-00261401
 MS-00261501
 Feb.2016

4/4

(4) END PROPERTIES

Item	Test method	Test result
Adhesion	TAIYO Internal Test Method Cross-cut tape stripping test	100 / 100
Pencil hardness	TAIYO Internal Test Method On copper foil, no Cu exposure	3H
Solder heat resistance	Solder float test : Rosin flux, 260deg.C/30sec (1cycle)	Passed
Solvent resistance	PGM-AC dipping, temp 20deg.C/20min, Scotch tape peeling test	Passed
Acid resistance	10vol % H ₂ SO ₄ , temp 20deg.C/20min, Scotch tape peeling test	Passed
Alkaline resistance	10wt% NaOH, temp 20deg.C/20min, Scotch tape peeling test	Passed
Electroless Ni/Au Plating resistance	TAIYO Internal Test Method Ni: 3um / Au: 0.03um	Passed
Bendability	TAIYO Internal Test Method Kapton, 180deg. Bending	No crack
Flame resistance	UL94VTM Flammability Test Kapton, double side coating	UL94VTM-0 equivalent

6. ATTENTION

*All test data shown above on this technical data sheet are based on our laboratory test result and only for reference, not guarantee the same on your process.

*All chemicals used in this product might have unknown toxicity. Please handle with your most care referring to the MSDS for use.

*No intentional use of RoHS 2.0subjected 10 substances (Lead, Cadmium, Mercury, Hexavalent-chromium, PBBs, PBDEs, DEHP, DBP, BBP and DIBP) for this product.